


# CEMENTED CARBIDE PLATES

**Excellent wear resistance  
and fracture resistance.**




# Carbide Materials (for cutting tools)

## ■ Cemented carbide grade classification

ISO	Work material	Grade	Grain size (μm)	Content (mass%)			Hardness		TRS (GPa)	Features
				WC	Co	Other	(HV)	(HRA)		
<b>P</b>	Steel	<b>UTi20T</b>	2-3	Bal.	9	19	1450	90.5	2.0	UTi20T grade has exceptional advantages of high fracture toughness with optimizing heat resistance and oxidation resistance.
<b>M</b>	Stainless steel									
<b>K</b>	Cast iron Ductile cast iron	<b>HTi10</b>	<1.0	Bal.	6	1	1700	92.0	3.2	HTi10 grade has exceptional advantages of high hardness and strength.
<b>N</b>	Non-ferrous metal									
<b>S</b>	Heat resistant alloy Titanium alloy	<b>TF15</b>	<0.9	Bal.	10	-	1550	91.0	4.0	TF15 grade has exceptional advantages of high hardness and toughness with optimizing high breakage resistance and strong edge sharpness.

## ● Comparison of structure





## ■ Cermet grade classification for automatic lathes

ISO	Work material	Grade	Content (mass%)			Hardness		Features
			TiCN	Co+Ni	Other	(HV)	(HRA)	
<b>P</b>	Steel	<b>NX55</b>	49	18	33	1500	91.2	Excellent wear resistance. Suitable for steel continuous machining.
		<b>TBF61</b>	53	19	28	1450	90.5	Excellent thermal shock and fracture resistance. Suitable for steel continuous machining.

## ■ Tips for automatic lathes

### Grade

UTi20T	HTi10	TF15	NX55	TBF61
○	○	○	○	○



Order Number	Dimensions (mm)				
	L	W	R	T	
<b>TLR-15x3TxR3</b>	15 ±1.0	3 ±0.5	R3	2-6	+0.5 0
<b>-15x4TxR3</b>	15 ±1.0	4 ±0.5	R3	2-6	+0.5 0
<b>-20x2TxR4</b>	20 ±1.0	2 ±0.5	R4	2-4	+0.5 0
<b>-20x3TxR3</b>	20 ±1.0	3 ±0.5	R3	2-6	+0.5 0
<b>-20x4TxR3</b>	20 ±1.0	4 ±0.5	R3	2-6	+0.5 0
<b>-20x5TxR3</b>	20 ±1.0	5 ±0.5	R3	2-6	+0.5 0



Order Number	Dimensions (mm)				
	L	W	R	T	
<b>TLR-20x6xR3</b>	20 ±1.0	6 ±0.5	R3	2-6	+0.5 0
<b>-25x4xR3</b>	25 ±1.0	4 ±0.5	R3	2-6	+0.5 0
<b>-30x4xR3</b>	30 ±2.0	4 ±0.5	R3	2-6	+0.5 0
<b>-30x3xR4</b>	30 ±2.0	3 ±0.5	R4	2-6	+0.5 0
<b>-30x4xR4</b>	30 ±2.0	4 ±0.5	R4	2-6	+0.5 0

Note) Please contact us for any geometry

# Cemented carbide plates

## Grade

UTi20T	HTi10	TF15	NX55	TBF61
○	○	○	×	×



Order Number	Dimensions (mm)					
	L		W		T	
TLB-8x3xT	8	±0.5	3	±0.3	2-4	+0.5 0
-8x5xT	8	±0.5	5	±0.3	2-7	+0.5 0
-8x6xT	8	±0.5	6	±0.3	2-8	+0.5 0
-8x7xT	8	±0.5	7	±0.3	2-8	+0.5 0
-8x8xT	8	±0.5	8	±0.3	2-8	+0.5 0
-9x6xT	9	±0.5	6	±0.3	2-8	+0.5 0
-9x7xT	9	±0.5	7	±0.3	2-8	+0.5 0
-9x8xT	9	±0.5	8	±0.3	2-6	+0.5 0
-10x2xT	10	±0.5	2	±0.3	2-4	+0.5 0
-10x3xT	10	±0.5	3	±0.3	2-8	+0.5 0
-10x4xT	10	±0.5	4	±0.3	2-8	+0.5 0
-10x5xT	10	±0.5	5	±0.3	2-8	+0.5 0
-10x6xT	10	±0.5	6	±0.3	2-4	+0.5 0
-10x7xT	10	±0.5	7	±0.3	2-8	+0.5 0
-10x8xT	10	±0.5	8	±0.3	2-7	+0.5 0
-10x9xT	10	±0.5	9	±0.3	2-6	+0.5 0
-10x10xT	10	±0.5	10	±0.3	2-10	+0.5 0
-11x4xT	11	±0.5	4	±0.3	2-7	+0.5 0
-11x5xT	11	±0.5	5	±0.3	2-8	+0.5 0
-11x6xT	11	±0.5	6	±0.3	2-6	+0.5 0
-11x8xT	11	±0.5	8	±0.3	2-8	+0.5 0
-11x9xT	11	±0.5	9	±0.3	2-8	+0.5 0
-11x11xT	11	±0.5	11	±0.4	2-8	+0.5 0
-12x2xT	12	±0.5	2	±0.3	2-7	+0.5 0
-12x5xT	12	±0.5	5	±0.3	2-8	+0.5 0
-12x7xT	12	±0.5	7	±0.3	2-8	+0.5 0
-12x8xT	12	±0.5	8	±0.3	2-8	+0.5 0
-12x9xT	12	±0.5	9	±0.3	2-8	+0.5 0
-12x10xT	12	±0.5	10	±0.3	2-10	+0.5 0
-12x12xT	12	±0.5	12	±0.4	2-8	+0.5 0
-13x4xT	13	±0.5	4	±0.3	2-6	+0.5 0
-13x6xT	13	±0.5	6	±0.3	2-8	+0.5 0
-13x7xT	13	±0.5	7	±0.3	2-8	+0.5 0
-13x8xT	13	±0.5	8	±0.3	2-8	+0.5 0
-13x9xT	13	±0.5	9	±0.3	2-7	+0.5 0
-13x10xT	13	±0.5	10	±0.3	2-8	+0.5 0
-13x12xT	13	±0.5	12	±0.4	2-10	+0.5 0
-13x13xT	13	±0.5	13	±0.4	2-7	+0.5 0
-14x3xT	14	±0.5	3	±0.3	2-8	+0.5 0
-14x5xT	14	±0.5	5	±0.3	2-8	+0.5 0



Order Number	Dimensions (mm)					
	L		W		T	
TLB-14x6xT	14	±0.5	6	±0.3	2-8	+0.5 0
-14x8xT	14	±0.5	8	±0.3	2-8	+0.5 0
-14x10xT	14	±0.5	10	±0.3	2-9	+0.5 0
-15x3xT	15	±0.5	3	±0.3	2-4	+0.5 0
-15x4xT	15	±0.5	4	±0.3	2-4	+0.5 0
-15x5xT	15	±0.5	5	±0.3	2-8	+0.5 0
-15x6xT	15	±0.5	6	±0.3	2-8	+0.5 0
-15x7xT	15	±0.5	7	±0.3	2-8	+0.5 0
-15x8xT	15	±0.5	8	±0.3	2-7	+0.5 0
-15x9xT	15	±0.5	9	±0.3	2-8	+0.5 0
-15x10xT	15	±0.5	10	±0.3	2-7	+0.5 0
-15x12xT	15	±0.5	12	±0.4	2-7	+0.5 0
-15x13xT	15	±0.5	13	±0.4	2-8	+0.5 0
-16x3xT	16	±0.5	3	±0.3	2-8	+0.5 0
-16x4xT	16	±0.5	4	±0.3	2-8	+0.5 0
-16x5xT	16	±0.5	5	±0.3	2-4	+0.5 0
-16x6xT	16	±0.5	6	±0.3	2-8	+0.5 0
-16x7xT	16	±0.5	7	±0.3	2-8	+0.5 0
-16x8xT	16	±0.5	8	±0.3	2-8	+0.5 0
-16x9xT	16	±0.5	9	±0.3	2-8	+0.5 0
-16x10xT	16	±0.5	10	±0.3	2-8	+0.5 0
-16x11xT	16	±0.5	11	±0.4	2-6	+0.5 0
-16x14xT	16	±0.5	14	±0.4	2-8	+0.5 0
-16x15xT	16	±0.5	15	±0.4	2-7	+0.5 0
-16x16xT	16	±0.5	16	±0.4	2-10	+0.5 0
-17x3xT	17	±0.5	3	±0.3	2-8	+0.5 0
-17x4xT	17	±0.5	4	±0.3	2-8	+0.5 0
-17x5xT	17	±0.5	5	±0.3	2-8	+0.5 0
-17x6xT	17	±0.5	6	±0.3	2-8	+0.5 0
-17x8xT	17	±0.5	8	±0.3	2-8	+0.5 0
-17x10xT	17	±0.5	10	±0.3	2-10	+0.5 0
-17x11xT	17	±0.5	11	±0.4	2-8	+0.5 0
-17x13xT	17	±0.5	13	±0.4	2-8	+0.5 0
-18x3xT	18	±0.5	3	±0.3	2-8	+0.5 0
-18x4xT	18	±0.5	4	±0.3	2-7	+0.5 0
-18x5xT	18	±0.5	5	±0.3	2-7	+0.5 0
-18x6xT	18	±0.5	6	±0.3	2-8	+0.5 0
-18x7xT	18	±0.5	7	±0.3	2-8	+0.5 0
-18x9xT	18	±0.5	9	±0.3	2-8	+0.5 0
-18x10xT	18	±0.5	10	±0.3	2-8	+0.5 0

Note) Please contact us for any geometry

## Cemented carbide plates

### Grade

UTi20T	HTi10	TF15	NX55	TBF61
○	○	○	×	×



Order Number	Dimensions (mm)					
	L		W		T	
TLB-18x13xT	18	±0.5	13	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-18x15xT	18	±0.5	15	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-18x18xT	18	±0.5	18	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-19x5xT	19	±0.5	5	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-19x8xT	19	±0.5	8	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-19x11xT	19	±0.5	11	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-19x13xT	19	±0.5	13	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x2xT	20	±0.5	2	±0.3	2-4	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x3xT	20	±0.5	3	±0.3	2-5	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x4xT	20	±0.5	4	±0.3	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x5xT	20	±0.5	5	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x6xT	20	±0.5	6	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x7xT	20	±0.5	7	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x8xT	20	±0.5	8	±0.3	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x9xT	20	±0.5	9	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x10xT	20	±0.5	10	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x12xT	20	±0.5	12	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x15xT	20	±0.5	15	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x18xT	20	±0.5	18	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-20x20xT	20	±0.5	20	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-21x3xT	21	±0.5	3	±0.3	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-21x7xT	21	±0.5	7	±0.3	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-21x8xT	21	±0.5	8	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-21x9xT	21	±0.5	9	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-21x13xT	21	±0.5	13	±0.4	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-21x20xT	21	±0.5	20	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-21x21xT	21	±0.5	21	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-22x3xT	22	±0.5	3	±0.3	2-6	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-22x5xT	22	±0.5	5	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-22x8xT	22	±0.5	8	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-22x12xT	22	±0.5	12	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-22x15xT	22	±0.5	15	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-22x22xT	22	±0.5	22	±0.4	2-26	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-23x4xT	23	±0.5	4	±0.3	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-23x8xT	23	±0.5	8	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-23x14xT	23	±0.5	14	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-24x10xT	24	±0.5	10	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-24x12xT	24	±0.5	12	±0.4	2-6	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-24x24xT	24	±0.5	24	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-25x4xT	25	±0.5	4	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$



Order Number	Dimensions (mm)					
	L		W		T	
TLB-25x6xT	25	±0.5	6	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-25x8xT	25	±0.5	8	±0.3	2-11	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-25x9xT	25	±0.5	9	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-25x10xT	25	±0.5	10	±0.3	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-25x11xT	25	±0.5	11	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-25x12xT	25	±0.5	12	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-25x15xT	25	±0.5	15	±0.4	2-10	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-25x17xT	25	±0.5	17	±0.4	2-10	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-26x4xT	26	±0.5	4	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-26x7xT	26	±0.5	7	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-26x8xT	26	±0.5	8	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-26x9xT	26	±0.5	9	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-27x5xT	27	±0.5	5	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-27x7xT	27	±0.5	7	±0.3	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-27x12xT	27	±0.5	12	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-28x11xT	28	±0.5	11	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-28x12xT	28	±0.5	12	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-28x14xT	28	±0.5	14	±0.4	2-14	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-28x15xT	28	±0.5	15	±0.4	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-29x3xT	29	±0.5	3	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-30x3xT	30	±0.5	3	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-30x5xT	30	±0.5	5	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-30x6xT	30	±0.5	6	±0.3	2-10	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-30x9xT	30	±0.5	9	±0.3	2-11	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-30x10xT	30	±0.5	10	±0.3	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-30x16xT	30	±0.5	16	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-30x20xT	30	±0.5	20	±0.4	2-10	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-30x25xT	30	±0.5	25	±0.5	2-14	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-31x4xT	31	±0.7	4	±0.3	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-31x5xT	31	±0.7	5	±0.3	2-13	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-31x6xT	31	±0.7	6	±0.3	2-10	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-31x21xT	31	±0.7	21	±0.4	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-32x12xT	32	±0.7	12	±0.4	2-15	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-33x5xT	33	±0.7	5	±0.3	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-33x12xT	33	±0.7	12	±0.4	2-7	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-33x18xT	33	±0.7	18	±0.4	2-11	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-33x22xT	33	±0.7	22	±0.4	2-10	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-35x4xT	35	±0.7	4	±0.3	2-8	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-35x8xT	35	±0.7	8	±0.3	2-12	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$
-35x10xT	35	±0.7	10	±0.3	2-14	$\begin{smallmatrix} +0.5 \\ 0 \end{smallmatrix}$

Note) Please contact us for any geometry

## Cemented carbide plates

### Grade

UTi20T	HTi10	TF15	NX55	TBF61
○	○	○	×	×



Order Number	Dimensions (mm)					
	L		W		T	
TLB-35x13xT	35	±0.7	13	±0.4	2-12	+0.5 0
-35x20xT	35	±0.7	20	±0.4	2-12	+0.5 0
-36x5xT	36	±0.7	5	±0.3	2-12	+0.5 0
-36x7xT	36	±0.7	7	±0.3	2-10	+0.5 0
-36x9xT	36	±0.7	9	±0.3	2-7	+0.5 0
-38x24xT	38	±0.7	24	±0.4	2-11	+0.5 0
-39x4xT	39	±0.7	4	±0.3	2-8	+0.5 0
-39x28xT	39	±0.7	28	±0.5	2-12	+0.5 0
-40x2xT	40	±0.7	2	±0.3	2-10	+0.5 0
-40x4xT	40	±0.7	4	±0.3	2-12	+0.5 0
-40x6xT	40	±0.7	6	±0.3	2-12	+0.5 0
-40x10xT	40	±0.7	10	±0.2	2-11	+0.5 0
-40x15xT	40	±0.7	15	±0.4	2-15	+0.5 0
-40x16xT	40	±0.7	16	±0.4	2-12	+0.5 0
-42x20xT	42	±0.7	20	±0.4	2-11	+0.5 0
-43x9xT	43	±0.7	9	±0.3	2-12	+0.5 0
-45x6xT	45	±0.7	6	±0.3	2-12	+0.5 0
-47x2xT	47	±0.7	2	±0.3	2-12	+0.5 0
-50x2xT	50	+1.5 0	2	+0.3 0	2-10	+0.5 0
-50x3xT	50	+1.5 0	3	+0.3 0	2-12	+0.5 0
-50x4xT	50	+1.5 0	4	+0.3 0	2-11	+0.5 0
-50x5xT	50	+1.5 0	5	+0.3 0	2-11	+0.5 0
-50x6xT	50	+1.5 0	6	+0.3 0	2-14	+0.5 0
-50x7xT	50	+1.5 0	7	+0.4 0	2-8	+0.5 0
-50x8xT	50	+1.5 0	8	+0.4 0	2-12	+0.5 0
-50x9xT	50	+1.5 0	9	+0.4 0	2-10	+0.5 0
-50x10xT	50	+1.5 0	10	+0.4 0	2-12	+0.5 0
-50x12xT	50	+1.5 0	12	+0.5 0	2-12	+0.5 0
-50x15xT	50	+1.5 0	15	+0.5 0	2-15	+0.5 0
-51x3xT	51	+1.5 0	3	+0.3 0	2-12	+0.5 0
-51x4xT	51	+1.5 0	4	+0.3 0	2-10	+0.5 0
-51x5xT	51	+1.5 0	5	+0.3 0	2-12	+0.5 0
-51x12xT	51	+1.5 0	12	+0.5 0	2-12	+0.5 0
-52x3xT	52	+1.5 0	3	+0.3 0	2-12	+0.5 0

Order Number	Dimensions (mm)					
	L		W		T	
TLB-52x4xT	52	+1.5 0	4	+0.3 0	2-12	+0.5 0
-55x6xT	55	+1.5 0	6	+0.3 0	2-12	+0.5 0
-55x20xT	55	+1.5 0	20	+0.5 0	2-12	+0.5 0
-55x30xT	55	+1.5 0	30	±1.0	2-11	+0.5 0
-60x2xT	60	+1.5 0	2	+0.3 0	2-13	+0.5 0
-60x3xT	60	+1.5 0	3	+0.3 0	2-10	+0.5 0
-60x6xT	60	+1.5 0	6	+0.3 0	2-10	+0.5 0
-60x30xT	60	+1.5 0	30	+0.6 0	2-11	+0.5 0
-65x35xT	65	+2.0 0	35	+0.8 0	2-15	+0.5 0
-70x4xT	70	+2.0 0	4	+0.3 0	2-13	+0.5 0
-70x7xT	70	+2.0 0	7	+0.4 0	2-11	+0.5 0
-80x2xT	80	+2.0 0	2	+0.3 0	2-12	+0.5 0
-80x7xT	80	+2.0 0	7	+0.4 0	2-10	+0.5 0
-81x3xT	81	+2.0 0	3	+0.3 0	2-13	+0.5 0
-81x4xT	81	+2.0 0	4	+0.3 0	2-11	+0.5 0
-87x27xT	87	+2.0 0	27	+0.6 0	2-11	+0.5 0
-100x2xT	100	+5.0 0	2	+0.5 0	2-12	+0.5 0
-100x6xT	100	±2.5	6	+0.5 0	2-12	+0.5 0
-100x8xT	100	±2.5	8	+0.5 0	2-12	+0.5 0
-103x2.5xT	103	+5.0 0	2.5	+0.5 0	2-12	+0.5 0
-103x3xT	103	+5.0 0	3	+0.5 0	2-12	+0.5 0
-103x4xT	103	+5.0 0	4	+0.5 0	2-12	+0.5 0
-103x5xT	103	+5.0 0	5	+0.5 0	2-12	+0.5 0
-110x2.5xT	110	±2.5	2.5	+0.5 0	2-12	+0.5 0
-110x3xT	110	±2.5	3	+0.5 0	2-12	+0.5 0
-110x4xT	110	±2.5	4	+0.5 0	2-12	+0.5 0
-110x5xT	110	±2.5	5	+0.5 0	2-12	+0.5 0
-110x6xT	110	±2.5	6	+0.5 0	2-12	+0.5 0
-120x3xT	120	±2.5	3	+0.5 0	2-12	+0.5 0
-120x4xT	120	±2.5	4	+0.5 0	2-12	+0.5 0
-120x5xT	120	±2.5	5	+0.5 0	2-12	+0.5 0
-140x2xT	140	±2.5	2	+0.5 0	2-12	+0.5 0
-140x3xT	140	±2.5	3	+0.5 0	2-12	+0.5 0
-140x4xT	140	±2.5	4	+0.5 0	2-12	+0.5 0


Note) Please contact us for any geometry

# Carbide Materials (for die & mold)


## ■ Cemented carbide grade classification

Grade	Grain size (μm)	Content (mass%)			Hardness		TRS (GPa)	Features
		WC	Co	Other	(HV)	(HRA)		
<b>MF20</b>	<0.6	Bal.	12	—	1700	92.0	4.4	MF20 grade has exceptional advantages of high strength and hardness with optimizing high wear resistance.
<b>GTi20</b>	<2.5	Bal.	11	—	1300	89.0	2.7	GTi20 grade is used for general wear resistant application. The series offers various wear-resistant tools and machine parts.

## ● Comparison of structure




**MF20**



**GTi20**

## ■ Cemented carbide plates for die & moli



Order Number	Dimensions (mm)					
	L		W		T	
<b>TLD-60x40xT</b>	60	±2.0	40	±2.0	3-10	+1 0
<b>-66x61xT</b>	66	±2.0	61	±2.0	3-15	+1 0
<b>-100x100xT</b>	100	±5.0	100	±5.0	3-20	+1 0
<b>-150x100xT</b>	150	±5.0	100	±5.0	3-20	+1 0

Note) Please contact us for any geometry

## ▲ MITSUBISHI MATERIALS CORPORATION

ADVANCED MATERIALS & TOOLS COMPANY  
7F, KFC BLDG., 1-6-1, YOKOAMI, SUMIDA-KU, TOKYO 130-0015, JAPAN  
TEL +81-3-5819-5315 FAX +81-3-5819-5310

<http://blank.mitsubishicarbide.com>

